Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-08-05-22** **Date: 09-03-19**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.
Agency	:	Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.
Customer Reference	:	EE(Project)/Ynk Zone/WO/94/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-19
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-03-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	235	235	4.7	95.3	90-100
3	10 mm	2470	2705	54.1	45.9	25-55
4	4.75 mm	2133	4838	96.8	3.2	0-10
5	Pan	162	5000	100	0	_

CIVIL PRO Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-08-05-22** **Date: 09-03-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.1	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.5	
3	Specific Gravity	2.67	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	24.5	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.8	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

End of Report

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2019-08-05-22** **Date: 09-03-19**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-03-19

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 07-03-19

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL PRO Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2019-08-05-22** **Date: 09-03-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-08-05-22** **Date: 11-03-19**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.
Agency	:	Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/94/18-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	07-03-19
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	07-03-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	254	254	1.7	98.3	90-100
3	20 mm	5422	5676	37.8	62.2	30-70
4	10 mm	4132	9808	65.4	34.6	10-35
5	4.75 mm	4854	14662	97.7	2.3	0-5
6	Pan	338	15000	100.0	0	---

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-08-05-22** **Date: 11-03-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.8	
3	Specific Gravity	2.68	_
4	Bulk Density(Loose) (Kg/l)	1.48	_
5	Bulk Density(Compacted) (Kg/l)	1.52	_
6	Water Absorption(%)	0.22	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2019-08-05-22** **Date: 11-03-19**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.
Agency	:	Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout,
Customer's Reference	:	EE(Project)/Ynk Zone/WO/94/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	08-03-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.95	–
2	Finess by Air permeablity method (m^2/kg,Min)	285.3	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	150 minutes	Not less than 30 minutes
6	Final Setting time	245 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 19/03/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	149.58 X 150.19 X 149.18	22465	**8.128**	569.5	25.4	25.5
2	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	150.02 X 149.93 X 149.18	22493	**8.789**	601.7	26.8	
3	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	150.75 X 150.45 X 150.94	22679	**8.046**	555.2	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilzoneperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 09/04/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	149.01 X 150.38 X 150.98	22409	**8.621**	740.5	33.0	33.0
2	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	151.63 X 150.82 X 149.22	22869	**8.823**	749.0	32.8	
3	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	149.24 X 150.75 X 149.90	22497	**8.679**	744.6	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

Page 1/1
****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 19/03/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	151.80 X 150.94 X 149.69	22913	**8.128**	588.7	25.7	25.5
2	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	149.90 X 150.12 X 149.93	22503	**8.789**	594.4	26.4	
3	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	150.86 X 149.92 X 150.10	22618	**8.046**	552.2	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 09/04/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	150.26 X 149.44 X 151.38	22455	**8.621**	751.8	33.5	33.3
2	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	150.90 X 149.54 X 149.53	22566	**8.823**	731.8	32.4	
3	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	149.67 X 151.62 X 150.46	22692	**8.679**	770.4	33.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@gmail.com, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 19/03/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	150.44 X 151.35 X 151.08	22769	**8.128**	589.8	25.9	
2	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	151.60 X 151.98 X 149.74	23041	**8.789**	621.3	27.0	25.7
3	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	149.51 X 151.75 X 151.17	22688	**8.046**	550.4	24.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 09/04/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	151.89 X 149.97 X 149.76	22779	**8.621**	763.2	33.5	33.1
2	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	150.47 X 150.98 X 151.60	22719	**8.823**	736.5	32.4	
3	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	150.74 X 151.48 X 149.83	22834	**8.679**	762.6	33.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer, Project Division, Yelahanka Zone, Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 19/03/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	151.01 X 150.76 X 149.93	22767	**8.128**	581.1	25.5	25.4
2	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	151.11 X 149.95 X 150.72	22659	**8.789**	602.1	26.6	
3	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	150.98 X 149.44 X 151.74	22562	**8.046**	542.6	24.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.com, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22** **Date: 09/04/2019**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	150.77 X 149.04 X 149.88	22471	**8.621**	763.2	34.0	33.4
2	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	151.66 X 150.22 X 149.85	22783	**8.823**	738.6	32.4	
3	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	149.36 X 151.71 X 151.33	22659	**8.679**	763.9	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-08-05-22**

Date: 19/03/2019

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.

Agency : Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.

Customer's Reference : EE(Project)/Ynk Zone/WO/94/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-03-19

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/03/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	150.68 X 150.07 X 150.48	22613	**8.128**	576.9	25.5	25.6
2	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	149.88 X 151.21 X 150.69	22662	**8.789**	610.8	27.0	
3	Cement Concrete Pavement	M30	12/03/2019	19/03/2019	151.81 X 150.22 X 151.65	22806	**8.046**	557.8	24.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY & STRUCTURAL
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 09/04/2019

Lab ID	:	**CP-2019-08-05-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.
Agency	:	Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/94/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	14-03-19
Customer ID	:	Cement Concrete Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	09/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	150.76 X 151.71 X 150.85	22872	**8.621**	759.7	33.2	33.2
2	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	151.15 X 149.49 X 149.59	22595	**8.823**	742.5	32.9	
3	Cement Concrete Pavement	M30	12/03/2019	09/04/2019	151.94 X 151.41 X 149.87	23005	**8.679**	772.7	33.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2019-08-05-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore. **Date: 05-04-19**
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Providing CC Camera and Improvements to Solid Waste Management in Ward No-11 Kuvempunagar.
Agency	:	Sri.S.Somashekar, #90, New No.441/15, Allasandra, GKVK Layout, Bangalore-560 065.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/94/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-03-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	08-03-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in / civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |